



DURAPOL

Moisture Cure Coatings Product Information Guide



A Division of Era Polymers Pty Ltd
2-4 Green Street
BANKSMEADOW NSW 2019
Tel: +612 9666 3888 | Fax: +612 9666 4805

General Description

Polycure's range of DURAPOL moisture cure coatings are durable and hard wearing. Available in a range of gloss levels DURAPOL coatings will result in a rich colour that enhances the natural look of the timber.

Advantages

Durable and abrasion resistant
Excellent flow and levelling
Enhances the natural colour of the timber

Recommended Use

Interior use only. Timber, particleboard, cork or concrete.

*Not suitable for exterior or wet area applications e.g. bathrooms or around swimming pools.
Caution: floor will be slippery when wet.*

Application Methods

Equipment: 6mm mohair roller and high quality brush

Coating Uncoated Timber, Parquetry or Cork

- Preparing the floor to a professional standard is essential to achieve the best results.
- Fill all nail holes with a water based putty, allow to dry.
- Sand uncoated floor with 120-150 grade sandpaper or screenback on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly. Take care to avoid scratching the surface.
- Apply a liberal first coat of DURAPOL Gloss or FASTASEAL 3030, 3535 or 3540 – (note: application of 3540 in colder temperatures is not recommended - refer to Polycure representative), Sealer using a 6mm mohair roller and good quality brush to cut in. Allow to dry overnight (min 8 hours to max 24 hours).
- Sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Allow to dry overnight. Vacuum all dust.
- Apply a second coat of DURAPOL Gloss. Allow to dry overnight (min 8 hours to max 24 hours).
- Sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Allow to dry overnight. Vacuum all dust.
- Apply the final coat of DURAPOL Gloss or Subdued Gloss.

Recoating coated Timber, Parquetry or Cork

- Clean floor with AQUACARE 8440 Floor Clean Concentrate.
- Sand uncoated floor with 120-150 grade sandpaper or screenback on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly. Take care to avoid scratching the surface.
- Apply a coat of DURAPOL using a 6mm mohair roller and good quality brush to cut in. Allow to dry overnight (min 8 hours to max 24 hours).
- Optional: Apply a second coat of DURAPOL after sanding the floor.

Note: Only pour sufficient coating to complete the job, replace the lid immediately as exposure to the environment can cause the product quality and performance to be affected. Do not return unused product to the can as this will cause the remaining material to increase in viscosity.

Ensure that sand paper and screenbacks are replaced regularly so that they continue to "cut" the floor. If they are worn they will burnish the floor which will compromise intercoat adhesion between coats and result in delamination.

Option: Recoating DURAPOL coatings with AQUAPRO 8270 Advance 2K Floor Finish.

The DURAPOL range of coatings can be over coated with AQUAPRO 8270 Advance 2K if required. The floor must be thoroughly cleaned and sanded with 120-150 grit sandpaper or screenback to provide a sound mechanical key which is important to achieve adhesion. Apply per the AQUAPRO 8270 Advance 2K directions.

Maintenance

After your floor has been coated, be sure to follow the guidelines below to minimise the risk of scratching and scuffing:

- | | |
|--|-------------------------------|
| • Walking on floor with socks or stockings | 24 hours |
| • Replacing furniture | 2-3 days (longer is possible) |
| • Replacing mats and rugs | 3-4 weeks |
| • Damp mopping | 2-4 weeks |

When the floor is dry enough to walk on (normally 24 hours), open all the doors and windows to circulate the air. This is important to ensure proper curing of the coating.

Ongoing Care:

- Place door mats outside all entrances and ideally a soft mat inside each entrance to help remove sand, grit and small stones from shoes. When sand and grit is walked over the floor it is abrasive and acts like sandpaper and will damage the floor.
- If possible, use mats in high traffic areas e.g. near the sink and/or oven and hot plates.
- Use floor protectors on furniture legs.
- Keep pet claws trimmed to minimise scratching.
- Regularly sweep the floor with an antistatic mop to prevent the build-up of grit. Be careful with vacuum cleaners as the cleaning heads and bristles could scratch the floor.
- Remove any spills immediately and spot clean as required.
- To avoid direct sunlight and to reduce fading and discolouration of the coating, use blinds and curtains.
- Wash the floor with a pH neutral cleaner designed for timber floors such as AQUACARE 8440 Floor Clean Concentrate.
- Do not use methylated spirits.
- Do not use too much water whilst mopping (damp mop only) as too much moisture can damage the timber.
- Do not use polishes or household cleaners as they may damage the floor.
- Avoid dragging furniture over timber floors.
- Avoid walking on the floor with stilettos at all times as these can dent the floor.

Warning: All coatings provide protection for the substrate, however no coating is indestructible and all coatings will mark or scratch. Sharp objects including sand and grit will scratch the surface of any coated floor. In high traffic commercial environments such as hair dressing salons, night clubs or taverns several factors need to be considered when choosing a coating system such as the amount of traffic, moisture, alcohol and chemicals likely to come into contact with the floor. A thorough cleaning and maintenance program must be implemented after the coating system has thoroughly dried to help to maintain the coating.

Handy Hints

- **High Humidity and Moisture:** All wood will swell and discolour if allowed to come into contact with water vapour. The protection provided by a coating is dependent on the moisture transmission of the coating and on the thickness of the dry coating film applied. Coated edges are usually the most vulnerable to damage either from the coating being removed or by inadequate film builds in high wear / traffic areas. Special care should always be given to sharp edges as coatings do not build well onto them, resulting in reduced protection in high moisture environments.
- **Damp Wood:** Do not apply coatings over damp wood (moisture content greater than 15%) as it may result in loss of adhesion, cracking or veneer checking of the wood.
- **High Humidity at Time of Application:** Application of coatings at high humidity will speed up the drying process and reduce the pot life.
- **Inter-coat Adhesion:** To ensure sound inter-coat adhesion, thoroughly sand between coats. To reduce the potential for adhesion failure in field, Mirotone strongly recommends you carry out regular and appropriate quality control testing of your production output.
- **Cold Temperature:** Application below 10°C will affect the drying and gloss level of the coating.

- Clear coatings do not permanently protect the substrate (in particular, wood) from the ageing / discolouration effects of temperature and sunlight. Even when UV absorbers are present in a coating they will sacrificially break down over time and eventually no longer help to protect the substrate.
- Over thinning the first coat may contribute to edge bonding or glueing. Users must satisfy themselves that the timber is properly acclimatised and has reached an equilibrium moisture content suitable for the planned in-service environment before coating.

Health & Safety

Before handling, refer to the Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated SDS and packaging label before using this product.

www.polycure.com.au