FUGRO TECHNICAL SERVICES LIMITED

MateriaLab Division, Fugro Development Centre.

5 Lok Yi Street, 17 M.S. Castle Peak Road, Tai Lam, Tuen Mun, N.T., Hong Kong.

: +852-2450 8233 Fax : +852-2450 6138 E-mail: matlab@fugro.com.hk

Website: www.materialab.com.hk



Client Ref. Report No.

102752ST100621(2)

Page

REPORT ON DETERMINATION OF LAMINATED SHEET TO IMPACT BY SMALL-DIAMETER BALL

Information Supplied by Client

Client

Sois Mendinni Group

Project

Testing of HPL

Sample Description

Sois Mendinni Laminate

Laboratory Information

Lab. Sample I.D.

ST100621/15-19

Date Received

14 October 2010

Date Tested

14 December 2010

Test Method

BS EN 438-2: 2005, Clause 20

Test Results

Lab. Sample I.D.		ST100521/15	ST100521/16	ST100521/17	ST100521/18	ST100521/19
Force (N)	10	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	15	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	20	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	25	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	30	No hairline cracks				
	35	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	40	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	45	Cracks shown on surface	No hairline cracks	No hairline cracks	No hairline cracks	No hairline cracks
	50	Cracks shown on surface				
Impact resistance		40	45	45	45	45

Remark: The test results relate only to the samples tested.

Checked By

Certified By: Letter Date: 23(1)24(0)

Chan Chun Wai Ivan

Manager (Product Testing Laboratory)